

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
22 January 2004 (22.01.2004)

PCT

(10) International Publication Number
WO 2004/007362 A1

(51) International Patent Classification⁷: C01B 31/02,
C23C 16/26, 16/54, B01J 23/74

[MY/GB]; 49 Middleham Road, Newton Hall, Durham
DH1 5QH (GB).

(21) International Application Number:
PCT/GB2003/003086

(74) Agent: SMART, Peter, J.; W.H. Beck, Greener & Co., 7
Stone Buildings, Lincoln's Inn, London WC2A 3SZ (GB).

(22) International Filing Date: 16 July 2003 (16.07.2003)

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0216654.4 17 July 2002 (17.07.2002) GB

(71) Applicant (*for all designated States except US*): CAM-
BRIDGE UNIVERSITY TECHNICAL SERVICES
LIMITED [GB/GB]; 16 Mill Lane, Cambridge CB2 1SB
(GB).

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): SHAFFER, Milo,
Sebastian, Peter [GB/GB]; Flat 4, 26 Kensington Gardens
Square, London W2 4BG (GB). WINDLE, Alan, H.
[GB/GB]; 15 Storeys Way, Cambridge CB3 0DP (GB).
JOHNSON, Brian, F., G. [GB/GB]; The Masters Lodge,
Fitzwilliam College, Huntingdon Road, Cambridge CB3
0DG (GB). GENG, Junfeng [CN/GB]; 127 Pheasant
Rise, Bar Hill, Cambridge CB3 8SD (GB). SHEPHARD,
Douglas [GB/GB]; Hartley Royd Farm, Luddenden,
Halifax, Yorkshire HX2 6SN (GB). SINGH, Charanjeet

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: CVD SYNTHESIS OF CARBON NANOTUBES

(57) Abstract: A method of production of carbon nanoparticles comprises the steps of: providing on substrate particles a transition metal compound which is decomposable to yield the transition metal under conditions permitting carbon nanoparticle formation; contacting a gaseous carbon source with the substrate particles; before, during or after said contacting step, decomposing the transition metal compound to yield the transition metal on the substrate particles; forming carbon nanoparticles by decomposition of the carbon source catalysed by the transition metal; and collecting the carbon nanoparticles formed.

WO 2004/007362 A1

10/521356

1

CVD SYNTHESIS OF CARBON NANOTUBES

The present invention relates to methods of synthesis of carbon nanoparticles, and to the carbon nanoparticles thus
5 produced.

Carbon nanoparticles have received a great deal of attention since the discovery of the C₆₀ buckminsterfullerene molecule (H. W. Kroto, J. R. Heath, S. C. O'Brien, R. F. Curl and R. E. Smally, Nature 318, 162 (1985)) and the carbon
10 nanotube (S. Ijima, Nature 354, 56 (1991)). Carbon nanoparticles are typically 1 to 100 nm in at least one dimension, carbon nanotubes however being up to a few millimetres in length. The explosion in C₆₀ research in the early 1990s was driven by the production of large quantities
15 (few milligrams) of the material by Kratschmer et al. (W. Kratschmer, L. D. Lamb, K. Fostiropoulos and D. R. Huffman, Nature 347, 354 (1990)) using a high pressure arc discharge method.

The remarkable mechanical and electronic properties
20 exhibited by carbon nanotubes have encouraged efforts to develop mass production techniques. As a result, carbon nanotubes are becoming increasingly available, and more attention from both academia and industry is focused on the application of carbon nanotubes in bulk quantities. These
25 opportunities include the use of carbon nanotubes as a conductive filler in insulating polymer matrices, and as reinforcement in structural materials. Other potential applications exploit the size of carbon nanotubes as a template to grow nano-sized, and hence ultra-high surface-to-

volume ratio, catalysts or aim to combine carbon nanotubes to form nano-electronic elements.

The high cost and low production volume of carbon nanotubes are at present prohibitive for them to be used as a filler material in most large-scale structural and electrical applications. Presently, several industrial and governmental projects are underway to mass produce several kilograms of single and multi-walled carbon nanotubes in a cost-effective manner. For example, the National Institute of Materials and Chemical Research (NIMCR) and Showa Denko K. K. in Japan recently announced a project to develop a mass-production method to produce several hundred kilograms of nanotubes per day.

Carbon nanotubes have been produced previously using various approaches including the laser or arc-discharge ablation of a carbon/catalyst mixture target.

For larger scale synthesis, the most promising methods have been based on chemical vapour deposition (CVD). CVD typically uses a cheap feedstock and has relatively low energy requirements, and has therefore attracted interest for the purposes of bulk synthesis. In CVD methods, a carbon containing gas is decomposed at high temperatures under the influence of a finely divided catalyst (usually iron, nickel, cobalt or other transition metals or alloys).

Catalyst particles may be manufactured in situ by the decomposition of metalloorganic compounds or may be inserted into the CVD furnace on a fixed substrate (W. E. Alvarez et al., Carbon 39 (2001) 547-558; WO00/17102; WO00/73205). For the growth of small nanotubes and single-walled nanotubes in

particular, very small metal clusters (around 1 nm) are required.

The catalyst may be in the form of a fragmented surface layer on a porous or non-porous macroscopic substrate (Ren et al., Bower et al., V I Merkulov, D H Lowndes, Y Y Wei et al., Andrews et al., and Cui et al.). As described in Kanzow et al, the catalyst may be a laser ablated nickel target exposed to a flow of reactant gas.

Alternatively, the catalyst may be in finely divided form. In W000/17102, the catalyst is constituted by nanometer sized metal particles supported on larger (10-20 nm) alumina particles. The particles are placed in the centre of a furnace and the carbon containing gas is passed over them.

In W000/73205, catalyst particles comprising two different metals supported on silica, alumina, magnesia, zirconia or zeolite are used, again placed in a tube within a furnace. It is also suggested that the metallic catalytic particles may be continuously fed to the furnace.

Many catalyst precursors known in the art are initially contaminated with carbon-containing surfactants (e.g. Pluronic 123™) derived from precursor solutions. Carbon is removed by calcination at elevated temperatures (typically around 500 °C) in air, to produce an oxide. Alternatively, oxides or other inorganic salts which decompose to oxides (e.g. nitrates and carbonates) are used directly as catalyst precursors. In either case, it is then usual to reduce the oxide to the metal in a further step (typically 700 °C in hydrogen).

In WO00/26138, catalyst nanoparticles are continuously produced within a furnace in the presence of reactant gas by decomposing a gaseous catalyst precursor (normally $\text{Fe}(\text{CO})_5$) in the presence of a 'nucleation agency'. This may be a
5 laser which provides some or all of the energy needed for photolysis of the catalyst precursor, or it may be a precursor moiety that stimulates clustering of catalyst atoms by decomposing more rapidly or binding to itself more strongly after dissociation. Typically, this is $\text{Ni}(\text{CO})_4$.

10 A continuing problem in this art is the control over the extent of the production of multi-walled nanotubes in preference to single walled nanotubes and the control of the diameter of the tubes. In CVD synthesis, fine structures, such as single walled nanotubes require very fine catalyst
15 particles with diameters similar to that of the synthesised material (typically about 1 nm). Maintaining the required catalyst particle size generally requires the use of a substrate to act as a carrier material to stabilise the catalyst itself. However, the production of very fine
20 supported catalyst particles prior to use in the nanotube synthesis is generally complex and expensive involving for example aggressive reagents and supercritical drying. Substantial problems arise in preventing nanoparticles from coalescing prematurely and the synthesis of such particles is
25 not suitable for scaled-up production.

The production of catalyst particles in situ in the reaction zone as in WO00/26138, where the catalyst particles are essentially unsupported, or where the nucleation of catalyst clusters is enhanced by the presence of Ni species
30 suffers from a lack of particle size control. Since the

particles are growing, the time at which they initiate nanotube growth may be critical.

Because the nucleation sites are formed in situ from individual Ni atoms and comprise only a few atoms (2 to 5
5 atoms) in total, the process offers little control over the size of the nucleating "particle", or of the size of the final catalyst clusters. There is no controlled templating of the catalyst by the structure of the substrate.

In a first aspect, the present invention provides a
10 method of production of carbon nanoparticles, comprising the steps of:

providing on substrate particles a transition metal
compound which is decomposable to yield the transition
metal under conditions permitting carbon nanoparticle
15 formation;
contacting a gaseous carbon source with the substrate
particles;
before, during or after the contacting step, decomposing
the transition metal compound to yield the transition
20 metal on the substrate particles and forming carbon
nanoparticles by decomposition of the carbon source
catalysed by the transition metal;
and
collecting the carbon nanoparticles formed.

25 The transition metal compound may contain more than one metallic element. Alternatively or additionally, a mixture of transition metal compounds may be used, and in this case the different transition metal compounds may contain different metallic elements.

Preferably, the transition metal compound is a transition metal salt. More preferably, the transition metal salt is a transition metal formate or oxalate.

The transition metal compound may be a transition metal carbonyl, more preferably a multi metal atom carbonyl. The transition metal carbonyls is preferably non-volatile, in the sense that it does not evaporate or sublime before decomposition takes place. The transition metal carbonyl may be a neutral compound or a salt. Preferred multi metal atom carbonyls contain from 13 to 55 metal atoms, for example a Ni_{38} carbonyl cluster. Suitable transition metal carbonyls for use in the invention may be made by the methods described in "Preparation, Characterisation and Performance of Encapsulated Copper-Ruthenium Bimetallic Catalysts Derived from Molecular Cluster Carbonyl Precursors." D. S. Shephard, T. Maschmeyer, G. Sankar, J. M. Thomas, D. Ozkaya, B. F. G. Johnson, R. Raya, R. D. Oldroyd, R. G. Bell, Chemistry Eu. J., 1998, 4, 1227; "Site-Directed Surface Derivatisation of MCM-41: Use of HRTEM and Molecular Recognition for Determining the Position of Functionality within Mesoporous Materials." D. S. Shephard, W. Zhou, T. Maschmeyer, J. M. Matters, C. L. Roper, S. Parsons, B. F. G. Johnson, M. J. Juer, Angew. Chem. Int. Ed., 1998, 37, 2718; "Preparation and Characterisation of a Highly Active Bimetallic (Pd-Ru) Nanoparticle Heterogeneous Catalyst." D. S. Shephard, R. Raja, G. Sankar, S. Hermans, S. Bromley, J. M. Thomas, B. F. G. Johnson, Chem. Comm. 1999, 1571; and "Supramolecular Ordering of Ruthenium Cluster Carbonyls in Mesoporous Silica." W. Zhou, D. S. Shephard, J. M. Thomas, T.

Maschmeyer, B. F. G. Johnson, R. G. Bell, Science, 1998, 280, 705.

Preferably, the transition metal is nickel, iron or cobalt.

5 Unlike the metal nitrates and similar salts used in the past, transition metal compounds used in this invention such as formats or oxalates are decomposable to the metal by heating without reduction, e.g. under a non-reducing atmosphere.

10 Suitable carbon-containing compounds for use as the carbon source include carbon monoxide and hydrocarbons, including aromatic hydrocarbons, e.g. benzene, toluene, xylene, cumene, ethylbenzene, naphthalene, non-aromatic hydrocarbons, e.g. methane, ethane, propane, butane, pentane, hexane,
15 cyclohexane, ethylene, propylene or acetylene, and oxygen-containing hydrocarbons, e.g. formaldehyde, acetaldehyde, acetone, methanol or ethanol, or a mixture of two or more thereof. In preferred embodiments, the carbon-containing compound is carbon monoxide (CO), methane, ethylene or
20 acetylene.

Preferably, the gaseous carbon source is passed over the substrate particles.

The carbon source may be mixed with one or more gases acting as a diluent such as inert gases, e.g. argon. The
25 carbon source may also be mixed with non carbon containing gases which play no direct role in the nanotube forming reaction but which play a contributory role, for instance by reacting with amorphous carbon as it is formed (as a by-product) and so keeping the reaction sites on the catalyst
30 clean and available for nanotube formation.

Gases which may be mixed with the carbon source include argon, hydrogen, nitrogen, ammonia, carbon dioxide or helium.

Preferred gas pressures for the gaseous carbon source and optional diluent are from 0.1 to 50 bar A, preferably
5 from 0.5 to 5 bar A, more preferably 1 to 2 bar A. The gaseous effluent from the furnace may be recycled, with or without clean up.

The substrate particles are preferably a suspended finely divided substrate material. In the most
10 straightforward case, the substrate particles are simply finely ground powders, for example oxides particles or silicate particles such as silica, alumina, CaSiO_x , calcium oxide and/or magnesium oxide. Finer materials such as gels and aerogels may be generated by a range of methods known to
15 those skilled in the art, such as fuming, colloidal processing, spray-drying, hydrothermal processing and so on. Particular benefit for the production of nanotubes may be derived by using structured substrate particles, particularly mesoporous silicas, anodised alumina membranes, or zeolites.
20 These materials have channels of similar dimensions to nanotubes, and can further guide both the deposition of catalyst and synthesis of nanotubes.

The finely divided substrate particles preferably have a size not smaller than 1 nm, e.g. not less than 5 nm. They
25 may contain not less than 10 atoms, e.g. not less than 15 to 20 atoms, perhaps not less than 50 atoms or 75 atoms.

Preferably, the transition metal compound is decomposed by heating, for example by heating to a temperature between 200 °C and 1000°C, more preferably between 600°C and 1000°C. To
30 stimulate decomposition of the catalyst precursor material,

an additional energy source (over and above the temperature of the furnace) may be locally applied. The source must be able to penetrate the loaded substrate powder. Such a source is preferably an intense light source, for example a laser or
5 an intense non-coherent light source such as a flash discharge lamp. Preferably, the light source is an ultraviolet light source. Alternatively, the additional energy source may be a plasma discharge or an arc discharge formed in the presence of the catalyst precursor material.

10 Preferably, the carbon nanoparticles are carbon nanotubes. More preferably, the carbon nanotubes are single walled carbon nanotubes.

Preferably, the method further comprises the initial step of impregnating the substrate particles with the transition
15 metal compound. More preferably, where a transition metal salt is used, impregnation is achieved using a solution of the transition metal salt.

Preferably, the method is continuous. In this case, the method may comprise the steps of:

20 continuously providing substrate particles;
fluidising the substrate particles with a flow of gaseous carbon source;
heating the transition metal compound on the substrate particles; and

25 collecting the carbon nanoparticles formed by elution.

Alternatively, the method may comprise the steps of:

continuously providing substrate particles to an upper part of an inclined surface;
contacting the substrate particles on the inclined
30 surface with a flow of gaseous carbon source;

heating the transition metal compound on the substrate particles; and
collecting carbon nanoparticles formed from a lower part of the inclined surface.

5 In a second aspect, the second invention relates to a method of production of carbon nanoparticles, comprising the steps of:

providing on substrate particles a transition metal oxalate, formate or multi metal atom carbonyl;
10 heating the transition metal oxalate, formate or multi metal atom carbonyl on the substrate particles;
contacting a gaseous carbon source with the substrate particles; and
collecting the carbon nanoparticles formed.

15 The features described in connection with the first aspect of the invention may also be used in connection with the second aspect of the invention. In a particularly preferred embodiment of the second aspect of the invention, the transition metal oxalate, formate or multi metal atom
20 carbonyl is nickel formate and the substrate particles comprise silica.

In a third aspect, the present invention relates to carbon nanoparticles formed by a method as described above.

The invention will be further illustrated by the
25 following non-limiting examples, with references to the drawings, in which:

Figure 1 shows the apparatus used in Examples 1, 3 4 and 6;
Figure 2 shows the product of Example 1:

30 a) SEM image

b) HRTEM image;

Figure 3 shows a Raman spectrum of the product of Example 2;
Figure 4 shows the product of Example 3:

a) SEM image

5 b) HRTEM image; and

Figure 5 shows the product of Example 4.

Apparatus

10 The apparatus 10 used in Examples 1, 3, 4 and 6 for the growth of carbon nanotubes is shown in Figure 1. The apparatus 10 comprises sources of argon 12, acetylene 14, hydrogen 16 and methane 18, connected to flow meters 20, 22, 24 and 26 respectively. Supply pipes 28, 30, 32 and 34 lead
15 from sources 12, 14, 16 and 18 into a drying container 36 containing calcium chloride. The outlet 38 of the drying container 36 is connected to a horizontal furnace 40 with heating elements 42, 44. Catalyst 46 contained in an alumina crucible 48 is positioned in the furnace 40 aligned with the
20 heating element 44. The outlet 50 of the furnace passes through a paraffin bubbler 52 and a beaker 54 containing activated carbon.

In Example 2, a modified version of the apparatus 10 of
25 Figure 1 is used, wherein the furnace 40 is replaced by a quartz tube (not shown).

Example 1

100 mg of silica powder (fumed silica from Aldrich Chemical Company, surface area 200 m²/g) was placed in a flask. To this was added 4.0 ml of aqueous nickel formate (1.09×10^{-2} M). The mixture was strongly stirred at room temperature for 5 30 minutes, then dried in an oven at 90 °C for 16 hours. The sample prepared in this way contained 2.5 wt% nickel loading relative to the silica support. The sample was ground gently by hand in an agate mortar to produce a uniform powder before introducing into the CVD furnace 40 (Figure 1) in an alumina 10 crucible 48 for the growth of CNTs. The growth of CNTs was performed using an argon-methane atmosphere (1:1 argon to methane) with a total gas flow rate of 400 ml/minute. The temperature was 860 °C. After 30 minutes the products were characterised by scanning electron microscopy (SEM), high 15 resolution transmission electron microscopy (HRTEM), and Raman spectroscopy. Figure 2 shows the SEM and HRTEM images of the nanotubes. The nanotubes were clean, pure singlewalled and almost monodisperse, with a diameter of about 1.0 nm. The nanotubes were mainly in the form of small 20 bundles although some individual nanotubes were observed.

Example 2

500 mg silica powder (fumed silica from Aldrich Chemical 25 Company, surface area 200 m²/g) was placed in a 100 ml beaker. To this was added 25 ml aqueous nickel formate (1.08×10^{-2} M). The mixture was strongly stirred at room temperature for 30 minutes, followed by further stirring at higher temperature (90 °C) for about 20 hours to dry the 30 sample. The metal loading in the prepared sample was 3.2 wt%

relative to the silica support. For nanotube growth, 26.49 mg of the sample was placed in the centre of a quartz tube preheated to 860 °C under argon atmosphere. Methane was then immediately introduced (1:1 argon to methane volume ratio, total flow rate of 400 ml/min) to initiate the nanotube growth. After 30 minutes of reaction, 25.37 mg of product was obtained. Raman spectroscopy indicated that the nanotubes were single-walled and monodisperse (Figure 3). The yield of the carbon nanotubes was 4.7 %, based on the formula:

$$\text{Yield \%} = (m_1 - m_0) / m_0 \times 100 \%$$

where: m_1 is mass of the catalyst powder after growth
 m_0 is mass of the catalyst powder after heating under identical conditions as for nanotube growth, except that no methane is introduced.

Example 3

20 mg silica fine powder (fumed silica from Aldrich Chemical Company, surface area 200 m²/g) was placed in a flask. To this was added 1.5 ml aqueous nickel formate (3.8 x 10⁻³ M). The mixture was strongly stirred at room temperature for 30 minutes, then dried in an oven at 90 °C for 16 hours. The prepared sample contained 1.7 wt% nickel loading relative to the silica support. The sample was ground gently by hand in an agate mortar to produce a uniform powder before introduction into the CVD furnace (Figure 1) in an alumina crucible for the growth of CNTs. The growth of CNTs was performed at 650 °C for 60 minutes using an acetylene and argon mixture (1:10 acetylene to argon). The total gas flow

rate was 220 ml/minute. The products were characterised by SEM and HRTEM. Figure 4 shows SEM and HRTEM images of the MWNTs produced. The diameters of the nanotubes produced were typically about 10 nm.

5

Example 4

When hydrogen (5:5:1 ratio of argon to hydrogen to acetylene, total flow rate of 220ml/min) was added to the gas stream of Example 3 during growth, high yields of MWNTs were obtained (Figure 4). The diameters of the nanotubes were found to increase to about 22 nm.

Example 5

15

Nickel 38 carbonyl cluster is prepared from smaller clusters by reaction in base or with a molecular template. For example, nickel 38 carbonyl cluster is prepared from nickel tetracarbonyl via nickel 6 carbonyl cluster as follows.

20 Nickel tetracarbonyl (5 ml) and potassium hydroxide (13 g) in methanol were stirred for 24 h under nitrogen. The resulting deep red suspension was evaporated under vacuum and the residue was dissolved in water. Upon addition of solid potassium bromide (20 g) and further evaporation under vacuum
25 to eliminate traces of methanol, red microcrystals of $K_2[Ni_6(CO)_{12}] \cdot xH_2O$ (nickel 6 carbonyl cluster) were obtained. To synthesise nickel 38 cluster, nickel 6 carbonyl cluster is treated with either platinum (II) chloride or K_2PtCl_4 in 1:1 molar ratio in acetonitrile. The $Ni_{38}Pt_6$ carbonyl cluster

salt can be separated from impurities as a result of differential solubility in the solvent.

5 Example 6

100 mg of silica powder (fumed silica from Aldrich Chemical Company, surface area 200 m²/g) is placed in a flask. To this is added 4.0 ml of dichloromethane dissolved nickel 38 carbonyl cluster (1.09×10^{-2} M). The mixture is strongly stirred at room temperature for 30 minutes, then dried in an oven at 90 °C for 16 hours. The sample is ground gently by hand in an agate mortar to produce a uniform powder before introducing into the CVD furnace 40 (Figure 1) in an alumina 15 crucible 48 for the growth of CNTs. The growth of CNTs is performed using an argon-methane atmosphere (1:1 argon to methane) with a total gas flow rate of 400 ml/minute. The temperature is 860 °C. After 30 minutes the products are characterised by scanning electron microscopy (SEM), high 20 resolution transmission electron microscopy (HRTEM), and Raman spectroscopy.

The one step process of the Examples is simple and cheap. The combinations of precursor and support particles 25 used are particularly effective at producing high yields of pure nanotubes.

Whilst the applicant does not wish to be bound by this theory, it is believed that the precursor molecules are adsorbed onto the surface of the support particles. At high 30 temperatures the transition metal salt precursor of Examples

1 to 4 thermally decomposes to produce metal nanoparticles of 1 - 3 nm diameter and gaseous side products. Such nanoparticles are chemically very active and serve as a catalyst for CNT growth. Transition metal carbonyl cluster precursors decompose by loss of the surface and connecting carbonyl ligands such that each cluster forms a metal nanoparticle. Each metal nanoparticle is of suitable size to nucleate an individual nanotube.

In general larger catalyst particles suppress single wall carbon nanotubes. Large catalyst particles are produced by sintering. This occurs if the catalyst is held at high temperature, particularly where there are high metal loadings or a smooth surface on which metal particles are mobile. Where sintering occurs, multi wall carbon nanotubes or encapsulated nanoparticles tend to be formed, probably depending on the size difference between the catalyst and the fundamental support particles. A strong attraction between substrate and catalyst favours nanotube growth. Temperatures which are too high lead to overcoating and production of multi wall carbon nanotubes, nanofibres or vapour grown carbon fibres. In the processes of the examples there is no need for additional heat treatment that can give rise to undesirable sintering effects.

The processes of the invention as illustrated above have several advantages over known CVD processes. First, in the processes of the Examples, there is no need for the usual calcination and reduction steps to produce the catalyst from the catalyst precursor. Secondly, water is used as the solvent in preparation of the catalyst precursors of Examples 1 to 4, and may also be used in the preparation of catalyst

precursors from transition metal carbonyl salts. The use of water rather than organic solvents has cost and environmental benefits. Thirdly, the precursors of Examples 1 to 4 are particularly easy to handle and to introduce onto the substrate as a result of their solubility in water, stability, low volatility, low cost and low toxicity. By comparison, conventional precursors such as nickel tetracarbonyl are difficult to handle.

The process of Example 6 has the advantage that each transition metal carbonyl cluster forms a metal nanoparticle of defined size. This gives optimal control over nanotube diameter and may allow chirality control.

The process of the Examples can be used to produce high-quality, high yield SWCNTs on an industrial scale. The process may be scaled up in a number of ways. For example, a bed of supported catalyst may be fluidised using suitable carbon-containing gas and reacted product collected by elution due to its reduced effective density, whilst fresh supported catalyst precursor is continuously added.

Alternatively, the supported catalyst precursor may be introduced to the top of a rotating, gently sloping cylindrical furnace tube and allowed to travel down the length of the heated furnace under a suitable atmosphere, growing nanotubes during the well-defined transit time. The quality of the nanotubes, in terms of diameter, length, ratio of SWNTs to MWNTs and amorphous carbon, can be controlled by controlling the catalyst loading, dispersion level in supports and the CVD growth parameters.

Although the invention has been described with reference to the Examples, it will be appreciated that various modifications are possible within the scope of the invention.

Claims:

1. A method of production of carbon nanoparticles,
comprising the steps of:
5 providing on substrate particles a transition metal
compound which is decomposable to yield the transition
metal under conditions permitting carbon nanoparticle
formation;
contacting a gaseous carbon source with the substrate
10 particles;
before, during or after said contacting step,
decomposing the transition metal compound to yield the
transition metal on the substrate particles;
forming carbon nanoparticles by decomposition of the
15 carbon source catalysed by the transition metal;
and
collecting the carbon nanoparticles formed.
2. A method as claimed in Claim 1, wherein the transition
20 metal compound is a transition metal salt.
3. A method as claimed in Claim 2, wherein the transition
metal salt is a transition metal formate or oxalate.
- 25 4. A method as claimed in Claim 1 or Claim 2, wherein the
transition metal compound is a transition metal
carbonyl.

5. A method as claimed in Claim 4, wherein the transition metal compound is a multi metal atom transition metal carbonyl.
- 5 6. A method as claimed in any one of the preceding claims, wherein the transition metal is nickel, iron or cobalt.
7. A method as claimed in any one of the preceding claims, wherein the gaseous carbon source is a hydrocarbon or carbon monoxide.
- 10
8. A method as claimed in Claim 7, wherein the gaseous carbon source is methane or acetylene.
- 15 9. A method as claimed in any one of the preceding claims, wherein the gaseous carbon source is passed over the substrate particles.
10. A method as claimed in any one of the preceding claims, wherein the gaseous carbon source is mixed with a diluent.
- 20
11. A method as claimed in Claim 10, wherein the diluent is argon.
- 25
12. A method as claimed in any one of the preceding claims, wherein the substrate particles comprise oxide particles and/or silicate particles.

13.A method as claimed in Claim 12, wherein the substrate particles comprise one or more of silica, alumina, CaSiO_x , calcium oxide or magnesium oxide.

5 14.A method as claimed in any one of the preceding claims, wherein the substrate particles are in the form of a fumed powder, a colloid, a gel or an aerogel.

10 15.A method as claimed in any one of the preceding claims, wherein the transition metal compound is decomposed by heating.

15 16.A method as claimed in Claim 15, wherein the transition metal compound is decomposed by heating to a temperature between 200 °C and 1000°C.

20 17.A method as claimed in Claim 16, wherein the transition metal compound is decomposed by heating to a temperature between 600 °C and 1000 °C.

18.A method as claimed in any one of the preceding claims, wherein the carbon nanoparticles are carbon nanotubes.

25 19.A method as claimed in any one of the preceding claims, wherein the carbon nanotubes are single walled carbon nanotubes.

30 20.A method as claimed in any one of the preceding claims, further comprising the initial step of impregnating the substrate particles with the transition metal compound.

21.A method as claimed in any one of the preceding claims,
where the method is continuous.

5 22.A method as claimed in Claim 21, comprising the steps of:
continuously providing substrate particles;
fluidising the substrate particles with a flow of gaseous
carbon source;
heating the transition metal compound on the substrate
10 particles; and
collecting the carbon nanoparticles formed by elution.

23.A method as claimed in Claim 21, comprising the steps of:
continuously providing substrate particles to an upper
15 part of an inclined surface;
contacting the substrate particles on the inclined
surface with a flow of gaseous carbon source;
heating the transition metal compound on the substrate
particles; and
20 collecting carbon nanoparticles formed from a lower part
of the inclined surface.

24.A method of production of carbon nanoparticles,
comprising the steps of:
25 providing on substrate particles a transition metal
oxalate, formate or multi metal atom carbonyl;
heating the transition metal oxalate, formate or multi
metal atom carbonyl on the substrate particles;
contacting a gaseous carbon source with the substrate

particles; and collecting the carbon nanoparticles formed.

25. A method as claimed in Claim 24, wherein the transition
5 metal oxalate, formate or multi metal atom carbonyl is
nickel formate and the substrate particles are silica
particles.

26. Carbon nanoparticles formed by a method as claimed in
10 any one of the preceding claims.

1/3




FIG. 1

2/3




FIG. 2




FIG. 3

BEST AVAILABLE COPY

3/3




FIG. 4




FIG. 5

BEST AVAILABLE COPY

INTERNATIONAL SEARCH REPORT

PCT/GB 03/03086

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C01B31/02 C23C16/26 C23C16/54 B01J23/74

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C01B C23C B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, INSPEC, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 333 016 B1 (HARWELL JEFFREY H ET AL) 25 December 2001 (2001-12-25) column 4, line 25 - line 33 column 5, line 25 - column 6, line 22; example 1 ---	1,2, 4-16, 18-21, 24-26
X	DE 100 43 891 A (INFINEON TECHNOLOGIES AG) 4 April 2002 (2002-04-04) paragraphs '0008!-'0011! paragraphs '0013!-'0017! --- -/--	1,2, 4-13, 15-18, 20,24,26

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

24 October 2003

Date of mailing of the international search report

10/11/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Marucci, A

INTERNATIONAL SEARCH REPORT

PCT/GB 03/03086

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	ROHMUND F ET AL: "A simple method for the production of large arrays of aligned carbon nanotubes" CHEMICAL PHYSICS LETTERS, 6 OCT. 2000, ELSEVIER, NETHERLANDS, vol. 328, no. 4-6, pages 369-373, XP002259154 ISSN: 0009-2614 the whole document	1,2,4, 6-11, 15-18, 21,24,26
X	HAFNER J H ET AL: "CATALYTIC GROWTH OF SINGLE-WALL CARBON NANOTUBES FROM METAL PARTICLES" CHEMICAL PHYSICS LETTERS, NORTH-HOLLAND, AMSTERDAM, NL, vol. 296, no. 1/2, 30 October 1998 (1998-10-30), pages 195-202, XP000869784 ISSN: 0009-2614 the whole document	1,2,6-9, 12-20,26
X	IVANOV V ET AL: "Catalytic production and purification of nanotubules having fullerene-scale diameters" CARBON, ELSEVIER SCIENCE PUBLISHING, NEW YORK, NY, US, vol. 33, no. 12, 1995, pages 1727-1738, XP004022410 ISSN: 0008-6223 "Experimental"	1,2,6, 10,15, 16,20, 24,26
X	KREUPL F ET AL: "Template grown multiwall carbon nanotubes" ELECTRONIC PROPERTIES OF MOLECULAR NANOSTRUCTURES: 15TH INTERNATIONAL WINTERSCHOOL/EUROCONFERENCE, KIRCHBERG, AUSTRIA, 3-10 MARCH 2001, no. 591, pages 231-234, XP002259155 AIP Conference Proceedings, 2001, AIP, USA ISSN: 0094-243X "Experimental set up" table 1	1-4, 6-10,12, 13, 15-18, 20,24,26

INTERNATIONAL SEARCH REPORT

PCT/GB 03/03086

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 6333016	B1	25-12-2001	AU 5462200 A 18-12-2000
		BR 0011106 A 05-03-2002	
		CA 2375887 A1 07-12-2000	
		CN 1360558 T 24-07-2002	
		EP 1192104 A1 03-04-2002	
		JP 2003500326 T 07-01-2003	
		WO 0073205 A1 07-12-2000	
		US 2002165091 A1 07-11-2002	
DE 10043891	A	04-04-2002	DE 10043891 A1 04-04-2002